

Attorney Docket No.: 130014/11922 (21635-0117)  
Application No.: 10/753,369

-2-

The claims are not amended. A clean copy of the claims is provided for reference.

1. (Original) A method for preparing a protected article, comprising the steps of  
providing the article;  
depositing a bond coat onto an exposed surface of the article; and  
producing a thermal barrier coating on an exposed surface of the bond coat, wherein  
the step of producing the thermal barrier coating includes the steps of  
depositing a primary ceramic coating onto an exposed surface of the bond  
coat, and  
depositing a stabilization composition onto an exposed surface of the primary  
ceramic coating, wherein the stabilization composition comprises a first element selected  
from Group 2 or Group 3 of the periodic table, and a second element selected from Group 5  
of the periodic table, and wherein the atomic ratio of the amount of the first element to the  
amount of the second element is at least 1:3.
2. (Original) The method of claim 1, wherein the step of providing the article  
includes the step of  
providing the article as a nickel-base superalloy article.
3. (Original) The method of claim 1, wherein step of providing the article  
includes the step of  
providing the article in the form of a component of a gas turbine engine.
4. (Original) The method of claim 1, wherein the step of depositing the bond  
coat includes the step of  
depositing a diffusion aluminide or an aluminum-containing overlay bond coat.
5. (Original) The method of claim 1, wherein the step of depositing the primary  
ceramic coating includes the step of  
depositing yttria-stabilized zirconia as the primary ceramic coating.
6. (Original) The method of claim 1, wherein the step of depositing the  
stabilization composition includes the step of

Attorney Docket No.: 130014/11922 (21635-0117)  
Application No.: 10/753,369

-3-

providing the first element selected from the group consisting of lanthanum, neodymium, and cerium.

7. (Original) The method of claim 1, wherein the step of depositing the stabilization composition includes the step of

providing the second element selected from the group consisting of tantalum and niobium.

8. (Original) The method of claim 1, wherein the step of depositing the stabilization composition comprises the step of

depositing the stabilization composition selected from the group consisting of lanthanum and tantalum, neodymium and tantalum, lanthanum and niobium, neodymium and niobium, and cerium and tantalum.

9. (Original) The method of claim 1, wherein the step of depositing the stabilization composition includes the step of

co-depositing the first element and the second element.

10. (Original) The method of claim 1, wherein the step of depositing the stabilization composition includes the step of

co-depositing the first element and the second element from a liquid solution

11. (Original) The method of claim 1, wherein the step of depositing the stabilization composition includes the step of

depositing the stabilization compound such that the atomic ratio of the amount of the first element to the amount of the second element is at least 1:1.

12. (Original) A method for preparing a protected article, comprising the steps of providing a nickel-base superalloy article that is a component of a gas turbine engine;

depositing a bond coat onto an exposed surface of the article; and

producing a thermal barrier coating on an exposed surface of the bond coat, wherein the step of producing the thermal barrier coating includes the steps of

depositing a yttria-stabilized zirconia primary ceramic coating onto an exposed surface of the bond coat,

Attorney Docket No.: 130014/11922 (21635-0117)  
Application No.: 10/753,369

-4-

infiltrating a stabilization composition into an exposed surface of the primary ceramic coating, wherein the stabilization composition comprises a first element selected from Group 2 or Group 3 of the periodic table, and a second element selected from Group 5 of the periodic table, and wherein the atomic ratio of the amount of the first element to the amount of the second element is at least 1:3.

13. (Original) The method of claim 12, wherein the step of depositing the primary ceramic coating includes the step of depositing yttria-stabilized zirconia having about 7 percent yttria by weight.

14. (Original) The method of claim 12, wherein the step of depositing the bond coat includes the step of depositing a diffusion aluminide or an aluminum-containing overlay bond coat.

15. (Original) The method of claim 12, wherein the step of infiltrating the stabilization composition includes the step of providing the first element selected from the group consisting of lanthanum, neodymium, and cerium.

16. (Original) The method of claim 12, wherein the step of infiltrating the stabilization composition includes the step of providing the second element selected from the group consisting of tantalum and niobium.

17. (Original) The method of claim 12, wherein the step of infiltrating the stabilization composition comprises the step of depositing the stabilization composition selected from the group consisting of lanthanum and tantalum, neodymium and tantalum, lanthanum and niobium, neodymium and niobium, and cerium and tantalum.

18. (Original) The method of claim 12, wherein the step of infiltrating the stabilization composition includes the step of co-depositing the first element and the second element.

Attorney Docket No.: 130014/11922 (21635-0117)  
Application No.: 10/753,369

-5-

19. (Original) The method of claim 12, wherein the step of depositing the stabilization composition includes the step of

depositing the stabilization compound such that the atomic ratio of the amount of the first element to the amount of the second element is at least 1:1.

20. (Original) A method for preparing a protected article, comprising the steps of providing the article;

depositing a bond coat onto an exposed surface of the article; and

producing a thermal barrier coating on an exposed surface of the bond coat, wherein the thermal barrier coating comprises

a primary ceramic coating on the exposed surface of the bond coat, and

a sintering-inhibitor region at a surface of the primary ceramic coating, wherein the sintering-inhibitor region comprises a first element selected from Group 2 or Group 3 of the periodic table, and a second element selected from Group 6 of the periodic table, and wherein the atomic ratio of the amount of the first element to the amount of the second element is at least 1:3.